

SECTION 703
AGGREGATES

703-2.03 AGGREGATE FOR BASE AND SURFACE COURSE. *In Table 703-1 replace the line for Degradation Value with the following:*

TABLE 703-1
AGGREGATE QUALITY PROPERTIES FOR BASE AND SURFACE COURSE

PROPERTY	BASE COURSE	SURFACE COURSE	TEST METHOD
Micro-Deval	15%, max.	15%, max.	AASHTO T 327

703-2.04 AGGREGATE FOR HOT MIX ASPHALT. *In Table 703-3 replace the line for Degradation Value with the following:*

TABLE 703-3
COARSE AGGREGATE QUALITY FOR HMA

Description	Specification	Type II, Class A	Type I, Type II Class B, Type III	Type IV	Type V	Type SP
Micro-Deval, max.	AASHTO T 327	18%	18%	18%	18%	18%

703-2.05 AGGREGATE FOR COVER COAT AND SURFACE TREATMENT. *In Table 703-5 replace the line for Degradation Value with the following:*

TABLE 703-5
QUALITY PROPERTIES FOR COVER COAT AND SURFACE TREATMENT

Micro-Deval	AASHTO T 327	15%, max.
-------------	--------------	-----------

703-2.09 SUBBASE. *In Table 703-8 replace the line for Degradation Value with the following:*

TABLE 703-8
QUALITY PROPERTIES FOR SUBBASE

Micro-Deval	AASHTO T 327	25%, max.
-------------	--------------	-----------